bodmerton
swiss quality clay

Technical data sheet

as of June 2026

article	495
description	tin oxide

Chemical analysis

SnO_2	> 99,9 %

Usage

in glazes:	The best opacifier for glazes. Adding 8–12% to a transparent base glaze produces soft faience glazes. Tin oxide increases the elasticity of the glazes and helps prevent hairline cracks. Tin glazes can be coloured to produce coloured overglazes. They react slightly to evaporating glaze components (pink discolouration).

Bodmer Ton AG
Holzrüti 1 · 8840 Einsiedeln · 055 418 28 58
info@bodmer-ton.ch · www.bodmer-ton.ch

V:1/26062026